AUSTRALIAN PIPE & TUBE

Product Test Certificate

161371 Certificate Number

4/10/2016 Date

PackFrom	PackTo	RHS/SHS/CHS Nominal Size (mm) d /do	b	t	L	Specification	Grade	Product Description
16273M10095	16273M10097	127.0	51.0	3.0	Any	AS1163: 2016	C350L0	Painted 127x51x3.0

Heat No.	Steel Supplier	Testing Authority/NATA (ILAC) No			Steel Chemical Analysis																Mechanical Test Results (Orientation-"L")									
		Tensile	Impact	Chemical	Analysis Type "L"/"P"	Testing Report No	C	P	Mn	Si	S	Ni	Cr	Mo	Cu	Al	Ti	Nb	V	B	CE	SiE	Testing Report No-Sample ID	Condition	Tensile Test			Impact Test at 0°C			
							(% x 100)																		YS	TS	E	1	2	3	Avg
																									MPa		%	Joules			
N50977	Import	MTL/19968		SS/19570	P	MANUAL	17	1	97	1.4	0.4	0	1	0	1	3.7	0.1	0.9	100	0.01	34	4	T3336-7167	A	486	555	25				

Notes:

1) CE=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15; **2)** SiE=Si+2.5P; **3)** Gauge Length for E= 5.65√So; **4)** Impact test piece thickness is 5 mm;

5) For t less than 6 mm L0 properties derived as per Cl 9.4.2.3 (b) of AS/NZS 1163; **6)** "L" = LADLE, "P" = PRODUCT

7) ALS=Australian Laboratory Services Industrial; MTL = Mec Test Laboratories; SS=Spectrometer Services Pty Ltd; BSL=Bluescope Steel;

8) The production date in the format yyddd constitutes the first 5 digits of the pack number and is printed on each length;

9) THE STEEL IS MADE BY BASIC OXYGEN OR AN ELECTRIC ARC PROCESS AND IS FULLY KILLED, CONTINOUSLY CAST AND FINE GRAINED. THE STRIP WAS HOT ROLLED AT THE HOT STRIP MILL.

Product Test Certificate

161371
Certificate Number

4/10/2016
Date

Packs covered by this certificate

Heat	Pack Numbers
N50977	16273M10095 16273M10096 16273M10097

Australian Pipe and Tube confirms that products listed above were manufactured, tested, and supplied in full compliance with the specifications quoted in this certificate.

Authorized signatory: L. DONALD
CEO