AUSTRALIAN PIPE & TUBE

Product Test Certificate

161452 Certificate Number

8/11/2016 Date

PackFrom	PackTo	RHS/SHS/CHS Nominal Size (mm) d /do	b	t	L	Specification	Grade	Product Description
16291M10030	16291M10037	100.0	100.0	4.0	Any	AS1163: 2016	C350L0	Painted 100x100x4.0

Heat No.	Steel Supplier	Testing Authority/NATA (ILAC) No			Steel Chemical Analysis																Mechanical Test Results (Orientation-"L")									
		Tensile	Impact	Chemical	Analysis Type "L"/"P"	Testing Report No	C	P	Mn	Si	S	Ni	Cr	Mo	Cu	Al	Ti	Nb	V	B	CE	SiE	Testing Report No-Sample ID	Condition	Tensile Test			Impact Test at 0°C			
							(% x 100)																		YS	TS	E	1	2	3	Avg
																									MPa		%	Joules			
16S704069	Import	MTL/19968		SS/19570	P	35803	15	1.7	58	4	1	<1	2	1	2	3.8	<1	<1	1	<0.05	26	8	T3354-7264	A	435	515	28				

Notes:

1) CE=C+Mn/6+(Cr+Mo+V)/5+(Ni+Cu)/15; **2)** SiE=Si+2.5P; **3)** Gauge Length for E= 5.65√So; **4)** Impact test piece thickness is 5 mm;

5) For t less than 6 mm L0 properties derived as per Cl 9.4.2.3 (b) of AS/NZS 1163; **6)** "L" = LADLE, "P" = PRODUCT

7) ALS=Australian Laboratory Services Industrial; MTL = Mec Test Laboratories; SS=Spectrometer Services Pty Ltd; BSL=Bluescope Steel;

8) The production date in the format yyddd constitutes the first 5 digits of the pack number and is printed on each length;

9) THE STEEL IS MADE BY BASIC OXYGEN OR AN ELECTRIC ARC PROCESS AND IS FULLY KILLED, CONTINOUSLY CAST AND FINE GRAINED. THE STRIP WAS HOT ROLLED AT THE HOT STRIP MILL.

Product Test Certificate

161452 Certificate Number

8/11/2016 Date

Packs covered by this certificate

Heat	Pack Numbers
16S704069	16291M10030 16291M10031 16291M10032
16S603697	16291M10037

Australian Pipe and Tube confirms that products listed above were manufactured, tested, and supplied in full compliance with the specifications quoted in this certificate.

Authorized signatory: L. DONALD

CEO